

# FUGEGUIDE

PRODUKT	TEKNISKE DATA									TRE		METALL				MINERALSKE MATERIALER						PLAST						FARGER							
	UV-bestendig	Overmalbar *	Bearbeidingsstid i min.	Herdetid mm/døgn	Elastisitet %	Temperaturbestandig etter utharding	Slipbarhet	Shore A	Fuktig underlag	Treverk	Teak	Zink/forsinkede overflater	Jern/stål	Aluminium	Rustfritt/Syrefast	Gips	Betong	Porebetong/Leca	Glass	Naturstein	Tegl	Hard PVC	Myk PVC	Polykarbonat	Glassfiberarmert polyester	Myk Termoplast (PP, PE)	Asfalt/tjære/bitumen	Isopor	Transparent	Hvit	Grå	Lys grå	Sort	Øvrige farger tilgjengelig	
<b>Sanitærsilikon</b>	++	-	10	3	25	+150	-	25	-	P	-	-	-	+	P	P	P	++	-	P	P	-	-	-	-	-	-	+	+	+	+	+	+	+	+
<b>Byggsilikon</b>	++	-	10-25	2	25	+120	-	17	-	+	-	+	+	+	P	++	P	++	-	P	+	-	+	-	-	-	+	+	+	+	+	+	+	+	+
<b>Akryl</b>	+	+	15	1	10	+80	0	30	-	+	-	-	-	-	P	+	P	-	-	+	+	-	-	-	-	-	+	-	+	+	-	-	-	-	-
<b>Malerakryl</b>	+	+	15	1	20	+80	0	30	-	+	-	-	-	-	P	+	P	-	-	+	+	-	-	-	-	-	+	-	+	-	-	-	-	-	-
<b>Tak-Tett</b>	++	+	15	1-2	25	+100	-	25	++	+	-	+	+	+	+	+	+	+	-	+	+	-	-	-	-	++	-	+	+	+	-	+	-	-	-
<b>MS Bygg Fugemasse</b>	+	+	10	2	25	+80	0	20	-	++	+	+	++	+	+	++	+	++	+	+	+	+	-	+	+	-	-	+	-	+	+	-	-	-	-
<b>Profug</b>	+	+	15	2	25	+90	0	26	-	++	+	+	++	+	+	++	+	++	+	+	+	+	-	+	+	-	-	+	-	+	+	-	+	-	-
<b>Klebmasse MS</b>	+	++	15	3	10	+80	+	60	0	+	+	+	++	+	+	+	++	+	+	+	+	-	+	+	-	-	+	-	+	+	-	+	-	-	-
<b>Klebmasse MS glassklar</b>	+	+	10	2	20	+90	-	38	-	+	-	+	+	+	+	+	0	+	0	+	+	-	+	+	-	-	+	+	-	-	-	-	-	-	-
<b>MS 40</b>	+	+	10-15	3	15	+100	+	60	0	++	+	+	++	+	+	+	++	+	+	+	+	-	+	+	-	-	+	-	+	+	+	+	+	+	+
<b>Brannhemmende akryl</b>	+	+	25	1	10	80	0	30	-	+	-	-	-	-	P	+	P	-	-	P	+	-	-	-	-	-	+	-	+	-	-	-	-	-	-
<b>Kleb og Tett Power</b>	++	++	40	3	15	-40-100	+	ca50	0	++	+	+	++	++	++	++	++	++	++	++	++	-	0	++	-	0	-	-	+	+	-	+	-	-	-

\* egne forsøk anbefales P egnet primer ++ meget godt egnet + godt egnet 0 mindre egnet - anbefales ikke

